

Kemisk Resistens

Chemical Resistance

PVC

Agro Nevada
America FLEX
America FLEX PESANTE
Arizona SUPERELASTIC
Arizona ARCTIC antistatico
Armorvin® HNA
Armorvin® HNP
Armorvin® HNT
Armorvinpress
Colorado
Florida
Iberflex
Idropool
Idropool MARINE WASTE
Jamaica S-M-L
Luisiana
Luisiana antistatico
Luisiana OL SUPERELASTIC
Luisiana OM
Luisiana OM SUPERELASTIC
Luisiana SUPERELASTIC
Metalflex I
Medium
Nevada PHF
Oregon
Oregon PESANTE SUPERELASTIC

Quadrapool
Ragno ACQUA 15 BAR
Ragno AIR 20 BAR
Ragno ANTIGELO
Ragno CR
Ragno INDUSTRY
Ragno N 20-40 BAR
Shark Hose
Soleil NEW P TRICÒ
Super Ragno N ACQUA
Super Ragno N 80 BAR
Termoresistente KLL125
Vacupress® CRISTAL
Vacupress® ENO PHF
Vacupress® FLEX
Vacupress® MARINE WASTE
Vacupress® SUPERELASTIC
Vinilflex N

PU

Aarmorvin® PU PHF
Armorvinpress PU
Armorvin® TOTAL PU OIL TPHF
Luisiana PU antistatico
Oregon PU ET
Oregon PU EST

Oregon PU ET antistatico
Oregon PU P EST antistat.
Polipo 15 BAR OIL
Ragno PU
Ragno PU conduttivo
Ragno TOTAL PU ET
Ragno TOTAL PU ROBOT
Super Arizona PU
Superflex PU
Superflex PU AS DIN/4102 B
Superflex PU CHR
Superflex PU HLR AS FOOD
Superflex PU L
Superflex PU LR
Superflex PU MR soffietto
Superflex PU COND. KZ DX
Superflex PU PLUS H
Superflex PU PLUS HMR
Superflex PU PLUS HPP/R
Superflex PU PLUS HPR
Superflex PU R
Termoresistente PU 200°C

TPV

Detroit
Superflex CALOR
Termoflex 150°C
Termoflex 150°C double
Termoflex 300°C
Termoflex 300°C double
Vacupress® CHEMI
Vacupress® FOOD

PVC OIL

America OIL
America OIL antistatico RIC
Arizona ARCTIC
Tubo Benzina
Vacupress® OIL
Vacupress® OIL PU

LLDPE

Oregon PE - PE AS
Super Ragno CHEMI 80 BAR
Vacupress® SUPERCHEMI

MERLETT

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
108-03-2	1-Nitropropan	1-Nitropropane		O				
67-63-0	1-Propanol	2-Propanol		S	S			
123-91-1	1,4-Dioxan	1,4-Dioxane		S				
104-76-7	2-Etylhexanol	2-Ethylhexanol		S	S			
616-45-5	2-Pirrolidone	2-Pirrolidone		S	S			
107-41-5	2,4-Pentandiol	2,4- Pentandiol		S	S			
75-07-0	Acetaldehyd	Acetaldehyde	U		O	U	U	S
60-35-5	Acetamid	Acetamide 5%				S		
67-64-1	Aceton	Acetone	U	O	O	U	U	U
75-05-8	Acetonitril	Acetonitrile	U	O			U	
75-36-5	Acetylklorid	Acetyl chloride		O				
/	Adipicestrar	Adipic esters			S			
124-04-9	Adipinsyra	Adipic acid	S				S	S
107-13-1	Akrylnitril	Acrylonitrile technical grade		S	S			
/	Aldehyder	Aldehydes				U		
/	Alifatiska estrar	Aliphatic esters	U				U	
591-87-7	Allylacetat	Allyl acetate			S			
107-18-6	Allylalkohol (2-propenol-1)	Allyl alcohol (2-propenol -1)	U	S			U	S
142-03-0	Aluminium acetat	Aluminium acetate	S				S	
7784-18-1	Aluminiumfluorid samtl. konc.	Aluminium fluoride all conc.			S			S
21645-51-2	Aluminiumhydroxid	Aluminium hydroxide	S				S	S
7446-70-0	Aluminiumklorid 25%	Aluminium chloride 25%			S	S		S
7446-70-0	Aluminiumklorid samtl. konc.	Aluminium chloride all conc.			S			S
13776-88-0	Aluminiummetafosfat	Aluminium metaphosphate			S			
10043-01-3	Aluminiumsulfat	Aluminium sulphate			S	U		S
/	Alunarter	Alums			S			

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
/	Aminer	Amines				U		
7664-41-7	Ammoniak (gas)	Ammonia (gas)	U		S		U	S
12125-01-8	Ammoniumfluorid	Ammonium fluoride			S			S
7664-41-7	Ammoniumhydroxid 5%	Ammonium hydroxide (liquid) 5%	S	S	S		S	S
7664-41-7	Ammoniumhydroxid 10%	Ammonium hydroxide (liquid) 10%	S	S	S		S	S
7664-41-7	Ammoniumhydroxid 25%	Ammonium hydroxide (liquid) 25% (26 Bé)	S	S	S		S	S
7664-41-7	Ammoniumhydroxid 28% (26 Bé)	Ammonium hydroxide (liquid) 28% (26 Bé)	S	S	S		S	S
7664-41-7	Ammoniumhydroxid 30%	Ammonium hydroxide (liquid) 30%		S	S			
7664-41-7	Ammoniumhydroxid konc.	Ammonium hydroxide conc.		S	S			S
506-87-6	Ammoniumkarbonat	Ammonium carbonate	S		S		S	S
12125-02-9	Ammoniumklorid 25%	Ammonium chloride 25%			S	S		S
12125-02-9	Ammoniumklorid mättad lösn.	Ammonium chloride sat.sol.			S			S
6484-52-2	Ammoniumnitrat 25%	Ammonium nitrate 25%	S		S	S	S	
6484-52-2	Ammoniumnitrat mättad lösn.	Ammonium nitrate sat.sol.	S		S		S	
7727-54-0	Ammoniumpersulfat	Ammonium persulphate	S		S		S	
7727-54-0	Ammoniumsulfat mättad lösn.	Ammonium sulphate sat.sol.			S	U	U	
10196-04-0	Ammoniumsulfid	Ammonium sulphide	S		S		S	
628-63-7	Amylacetat	Amyl acetate	U		S		U	U
71-41-0	Amylalkohol	Amyl alcohol	S	S	S		S	S
131-18-0	Amylftalat	Amyl Phthlate			U			
543 -59-9	Amylklorid	Amyl chloride			U			U
62-53-3	Anilin	Aniline		S	S			U
/	Animalisk olja	Animal oil		O	S	U		O
/	Animaliska fetter	Animal fats				S		
10025-91-9	Antimontriklorid	Antimony trichloride	S		S		S	
/	Aromaitic kolväten	Aromaitic hydrocarbons	U	U	U		U	

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
7778-39-4	Arseniksyra	Arsenic acid all. conc.			S			S
/	Asfalt	Asphalt			S			U
50-81-7	Askorbinsyra	Ascorbic acid 10%			S			S
64-19-7	Ättiksyra 3%	Acetic acid 3%	S	S	S	poliether S poliester O	S	O
64-19-7	Ättiksyra 5%	Acetic acid 5%	S	S	S		S	O
64-19-7	Ättiksyra 10%	Acetic acid 10%	S	S	S		S	O
64-19-7	Ättiksyra 30%	Acetic acid 30%	O	S	S	U	O	
64-19-7	Ättiksyra 50%	Acetic acid 50%	O	S	S	U	O	O
64-19-7	Ättiksyra 80%	Acetic acid 80%	O	S		U	O	U
64-19-7	Ättiksyra konc.	Acetic acid conc.		S		U		U
108-24-7	Ättiksyraanhydrid	Acetic anhydride	U		U		U	
12230-71-6	Bariumhydroxid	Barium hydroxide sat. sol.			S			S
513-77-9	Bariumkarbonat	Barium carbonate sat. sol.			S			S
10361-37-2	Bariumklorid	Barium chloride sat. sol.			S			S
7727-43-7	Bariumsulfat mättad lösn.	Barium sulphate sat.sol.			S			S
21109-95-5	Bariumsulfid mättad lösn.	Barium sulphide sat.sol.			S			S
100-52-7	Bensaldehyd	Benzaldehyde		O	O	U		U
71-43-2	Bensen	Benzene	U		U		U	U
/	Bensin / Bensin	Petrol / Gasoline				O / S	O	U
65-85-0	Bensoesyra	Benzoic acid	O		S		O	S
100-51-6	Bensylalkohol	Benzyl alcohol	U				U	
76-93-7	Benzilsyra	Benzilic acid		S				
10028-24-7	Bisodic fosfat	Bisodic phosphate			S			
/	Bisulphates och träffade Bisulphates	Bisulphates and met. Bisulphates	S				S	
/	Bläck	Ink			S			S
301-04-2	Blyacetat	Lead acetate			S			S

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
10099-74-8	Blynitrat	Lead nitrate			S			
/	Bomullsfröolja	Cottonseed oil			S			
1303-96-4	Borax 5%	Borax 5%	S		S	S	S	
1303-96-4	Borax konc.	Borax conc.	S		S		S	
10043-35-3	Borsyra 5%	Boric acid 5%	S		S	S	S	S
10043-35-3	Borsyra konc.	Boric acid conc.	S		S		S	S
7637-07-2	Bortrifluorid	Boron trifluoride			S			S
7726-95-6	Brom, flytande	Bromine, liquid			U			
108-86-1	Brombensen	Bromobenzene		U	U	U		
10035-10-6	Bromidric syra 30%	Bromidric acid 30%	S		S		S	
10035-10-6	Bromidric syra 50%	Bromidric acid 50%			S			
10035-10-6	Bromvätesyra vattenlös. 30%	Hydrobromic acid aq. soln. 30%	S		S		S	S
10035-10-6	Bromvätesyra vattenlös. 50%	Hydrobromic acid aq. soln. 50%			S			S
106-99-0	Butadien	Butadiene						
106-97-8	Butan	Butane gas						U
/	Butandiol 10%	Butandiol 10%			S			
/	Butandiol 50%	Butandiol 50%			S			
/	Butandiol 100%	Butandiol 100%	U		S		U	
/	Butanol (vatten)	Butanol (water)			S			S
123-86-4	Butylacetat	Butyl acetate		S	S			S
123-86-4	Butylakrylat	Butyl acrilate			S			
/	Butylalkohol	Butyl alcohol	O		S	S	O	S
109-73-9	Butylamin	Butylamine				O		
85-68-7	Butylbensylftalat (BBP)	Butyl benzyl phthalat (BBP)			O			
111-76-2	Butylglykol	Butyl glycol			S			
/	Cider	Cider			S			S

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
77-92-9	Citronsyra 5%	Citric acid 5%	S		S	S	S	S
77-92-9	Citronsyra mättad lösn.	Citric acid sat. sol.			S			S
74-90-8	Cyanidric syra	Cyanidric acid			S			
110-82-7	Cyklohexan	Cyclohexane	U	U	S	O	U	O
108-93-0	Cyklohexanol	Cyclohexanol		S	S	U		S
108-94-1	Cyklohexanon	Cyclohexanone	U			U	U	S
91-17-8	Dekalin	Decalin		U				
9004-53-9	Dextrin	Dextrin	S		S		S	S
50-99-7	Dextros	Dextrose	S		S		S	S
11071-47-9	Di-isobutylene	Di-isobutylene		U				
68515-49-1 53306-54-0	Di-isodecylftalat och isomerer	Di-isodecyl phathlate and isomers	U	S		O	U	
117-81-7	Di-isoktylftalat	Di-isooctyl phathlate	U	S	O	O	U	S
28553-12-0 68515-48-0	Di-isononylftalat och isomerer	Diisononyl phatalate and isomers	U	S	O	O	U	
108-20-3	Di-isopropyl-eter	Di-isopropyl-ether		O				
/	Diazo salter	Diazo salts			S			
74-95-3	Dibrom metan	Dibromo methane		U	U			
142-96-1	Dibutyleter	Dibutylether		S	S			
84-74-2	Dibutylftalat	Dibutylphthalate		O	O			
/	Dieselolja och biodiesel	Diesel oil and biodiesel				S	S	
109-89-7	Dietylamin	Diethylamine				U		
111-46-6	Dietylglykol	Diethylene glycol		S	S	O		S
60-29-7	Dietyleter	Diethyl ether				U		
60-29-7	Dietyleter	Diethylether		S				
96-22-0	Dietylketon	Diethyl ketone	U		O		U	
110-99-6	Diglykolsyra	Diglycolic acid			S			S
106-46-7	Diklorbensen	Dichlorobenzene			U			U

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
1300-21-6	Dikloretan	Dichloroethane			U	S		
124-40-3	Dimetylamin	Dimethyl amine			U			U
67-64-1	Dimetylformaldehyd	Dimethylformaldehyde		S				
68-12-2	Dimetylformamid	Dimethyl formamide	U	S		U	U	
67-68-5	Dimetylsulfoxid	Dimethylsulfoxide			S			
123-79-5	Dioktyladipat	Diocetyl adipate		S				
122-62-3	Dioktylsebacat	Diocetyl sebacate				S		
123-91-1 505-22-6	Dioxan	Dioxane (all isomers)	U				U	
25265-71-8	Dipropyleneglycol	Dipropyleneglycol		S				
112-53-8	Dodekanol	Dodecanol	S				S	
/	Emulgeringsmedel	Emulsifiers	S				S	
/	Emulsioner, fotografisk	Emulsions, photographic			S			
/	Epoxiharts	Epoxy resin				U		
74-84-0	Etan	Ethane				O		
106-93-4	Eten-bromid	Ethylene bromide	U				U	U
95-92-1	Etyl-oxalat	Ethyl oxalate				S		
141-78-6	Etylacetat	Ethyl acetate	U	O	O		U	
140-88-5	Etylakrylat	Ethyl acrylate	U	S			U	
64-17-5	Etylalkohol 10%	Ethylic alcohol 10%	S	S	S		S	
64-17-5	Etylalkohol 35%	Ethylic alcohol 35%	S	S	S		S	
64-17-5	Etylalkohol 40%	Ethylic alcohol 40%	S	S	S		S	
64-17-5	Etylalkohol 50%	Ethylic alcohol 50%		S	S	O		
64-17-5	Etylalkohol 96%	Ethylic alcohol 96%	U	S	S	U	U	U
64-17-5	Etylalkohol max. konc.	Ethylic alcohol max conc.	U	S	S	U	U	
100-41-4	Etylbensen	Ethyl benzene			U			
107-21-1	Etylenglykol	Ethylene glycol	S	S	S	S	S	S

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
60-29-7	Etyleter	Ethyl ether			U	U		U
75-00-3	Etylklorid	Ethyl chloride		U	U			U
108-95-2	Fenol	Phenol		S		U		U
62-53-3	Fenylamin	Phenylamine				S		
7705-08-0	Ferriklorid	Ferric chloride			S	S		S
10421-48-4	Ferrinitrat	Ferric nitrate			S			S
/	Fettsyror (> C6)	Fatty acids (>C6)	S					U
16872-11-0	Fluoborsyra	Fluoboric acid, acq.			S			S
7782-41-4	Fluor, gasformig	Fluorine, gaseous			U			U
16984-48-8	Fluorid	Fluoride	U				U	
16961-83-4	Fluorkiselsyra, acq.	Fluorosilic acid, acq.			S			S
16961-83-4	Fluorosilic syra	Fluorosilic acid			S			
7664-39-3	Fluorvätesyra 4%	Hydrofluoric acid 4%	S		S		S	S
7664-39-3	Fluorvätesyra 20%	Hydrofluoric acid 20%	O		S	U	O	S
7664-39-3	Fluorvätesyra 30%	Hydrofluoric acid 30%	O		S	U	O	S
7664-39-3	Fluorvätesyra 40%	Hydrofluoric acid 40%	U		S	U	U	S
7664-39-3	Fluorvätesyra 60%	Hydrofluoric acid 60%	U		S	U	U	S
7664-39-3	Fluorvätesyra 85%	Hydrofluoric acid 85%			S			S
7664-41-7	Flytande ammoniak	Liquid ammonia		S				
/	Flytande tvål	Liquid soaps	S			U	S	
50-00-0	Formaldehyd 20%	Formaldehyde 20%			S	U	S	S
50-00-0	Formaldehyd 37%	Formaldehyde 37%	S		S	U	S	S
50-00-0	Formaldehyd 40%	Formaldehyde 40%	O		S	U	O	S
75-12-7	Formamid	Formamide		S				
7664-38-2	Fosforsyra 5%	Phosphoric acid 5%	S		S		S	S
7664-38-2	Fosforsyra 20%	Phosphoric acid 20%	S		U		S	S

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
7664-38-2	Fosforsyra 30%	Phosphoric acid 30%	S		U		S	S
7664-38-2	Fosforsyra 50%	Phosphoric acid 50%			S			S
7664-38-2	Fosforsyra 80%	Phosphoric acid 80%			S			S
/	Fotogen	Kerosene	O		O	S	S	U
/	Fotografiskt lösning	Photographic solution			S			S
75-69-4	Freon 11	Freon 11		U		U		
75-71-8	Freon 12	Freon 12		U		S		S
75-45-6	Freon 22	Freon 22		U		U		
/	Fruktkött	Fruit pulps			S			S
7776-48-9	Fruktos	Fructose acq.	S		S		S	S
110-00-9	Furan	Furan		O				
98-01-1	Furfural	Furfural			U			
98-00-0	Furfurylalkohol	Furfuryl alcohol			U			
149-91-7	Gallussyra	Gallic acid			S			
1401-55-4	Garvsyra	Tannic acid			S			S
/	Gas, naturlig, teknisk kvalitet	Gas, natural, technical grade			S			U
/	Gasol	Liquefied petroleum gas	O					
/	Gelatin	Gelatine				S		
5996-10-1	Glukos	Glucose			S			S
56-81-5	Glycerin	Glycerine	S		S	S	S	
56-81-5	Glycerol	Glycerol	S	S			S	S
/	Glykoler	Glycols, commercial mix			S	O		S
79-14-1	Glykolsyra	Glycolic acid			S			S
/	Havsvatten	Sea water	S	S	S	S	S	S
142-82-5	Heptan	Heptane			S			U
118-74-1	Hexaklorobensen	Hexachlorobenzene			S			

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
110-54-3	Hexan	Hexane	U		S	S	U	
/	Hexanol, tertiär	Hexanol, tertiary			S			
/	Hydraulolja	Hydraulic oils				S		
123-31-9	Hydrokinon	Hydroquinone			S			
7790-92-3	Hypokloritsyra vattenlös. konc.	Hypochlorous acid aq. soln. conc.			S			
7790-92-3	Hypoklorsyra 20%	Hypochlorous acid 20%	S		O		S	O
540-84-1	Isooktan	Isooctane				S		
67-63-0	Isopropylalkohol	Isopropyl alcohol	S			O	S	
108-20-3	Isopropyleter	Isopropyl ether				S		
7758-94-3	Järnklorid	Ferrous chloride			S			S
7720-78-7	Järnsulfat	Ferrous sulphate			S			S
/	Jäst	Yeast			S			
/	Jod (lösning i Kaliumjodid)	Iodine (solution in Potassium iodide)			O			
/	Kaffe	Coffee			S			
/	Kalcium bisulphide	Calcium bisulphide		S				
10137-74-3	Kalcium klorat	Calcium chlorate			S			S
20548-54-3	Kalcium sulfid	Calcium sulphide				S		
/	Kalcium, natrium-och litiumfetter	Calcium, sodium and lithium fats				S		
62-54-4	Kalciumacetat	Calcium acetate	S				S	
1305-62-0	Kalciumhydroxid	Calcium hydroxide	S		S		S	S
7778-54-3	Kalciumhypoklorit	Calcium hypochlorite	S		S			S
471-34-1	Kalciumkarbonat	Calcium carbonate			S			S
10043-52-4	Kalciumklorid 20%	Calcium chloride 20%	S	S	S	S	S	S
10043-52-4	Kalciumklorid 25%	Calcium chloride 25%	S		S	S	S	S
10043-52-4	Kalciumklorid mättad lösn.	Calcium chloride sat.sol.	S		S		S	S
10124-37-5	Kalciumnitrat 50%	Calcium nitrate 50%			S	S		S

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
10124-37-5	Kalciumnitrat konc.	Calcium nitrate conc.				S		
1305-78-8	Kalciumoxid	Calcium oxide			S			
13397-24-5	Kalciumsulfat	Calcium sulphate			S			S
13746-66-2	Kalium hexacianoferrate (III)	Potassium hexacianoferrate (III)			S			
13769-41-0	Kalium-perklorat	Potassium perchlorate			S			S
7778-74-7	Kalium-perklorat	Potassium perchlorate			S			S
298-14-6	Kaliumbikarbonat	Potassium bicarbonate			S			S
7758-02-3	Kaliumbromid	Potassium bromide			S			S
151-50-8	Kaliumcyanid	Potassium cyanide			S			S
7778-50-9	Kaliumdikromat	Potassium dichromate 40%	S		S	S	S	S
7778-50-9	Kaliumdikromat samtl. konc.	Potassium dichromate all conc.	S			S	S	S
7789-23-3	Kaliumfluorid	Potassium fluoride			S			S
13943-58-3	Kaliumhexacyanoferrat (II)	Potassium hexacyanoferrate (II)			S			
1310-58-3	Kaliumhydroxid 5%	Potassium hydroxide 5%	S	S	S	S	S	S
1310-58-3	Kaliumhydroxid 10%	Potassium hydroxide 10%	S	S	S		S	S
1310-58-3	Kaliumhydroxid 50%	Potassium hydroxide 50%	S		S		S	S
1310-58-3	Kaliumhydroxid konc.	Potassium Hydroxide conc.	S		S		S	
1310-58-3	kaliumhypoklorit satt. Sol.	potassium Hypochlorite sat. Sol.			O			S
584-08-7	Kaliumkarbonat	Potassium carbonate			S			S
3811-04-9	Kaliumklorat	Potassium chlorate			S			S
7447-40-7	Kaliumklorid	Potassium chloride			S	S		S
7789-00-6	Kaliumkromat	Potassium chromate 40%			S			S
7757-79-1	Kaliumnitrat	Potassium nitrate			S	S		
7722-64-7	Kaliumpermanganat	Potassium permanganate			S			U
7727-21-1	Kaliumpersulfat	Potassium persulphate			S			S
7727-21-1	Kaliumsulfat	Potassium sulphate			S	S		S

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistent O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
1312-73-8	Kaliumsulfid (konc.)	Potassium sulphide (conc.)			S			S
10117-38-1	Kaliumsulfit (konc.)	Potassium sulphite (conc.)			S			
/	Kamfer olja	Camphor oil			U			
/	Kaprolakton	Caprolactone		S	S			
9000-71-9	Kasein	Casein	S				S	
1343-98-2	kiselsyra	Silicicacid, acq.			S			S
7782-50-5	Klor 100 % torr gas	Chlorine 100% dry gas			O			U
7782-50-5	Klor flytande	Chlorine liquid			U			
7782-50-5	Klor fuktig	Chlorine moist				U		U
/	Klor vatten	Chlorine water SAT. SOL. 2%			S			
79-11-8	Klorättiksyra	Chloracetic acid	U				U	
108-90-7	Klorbensen	Chlorobenzene			U			U
/	Klorerade lösningsmedel	Chlorinated solvents	U				U	
67-66-3	Kloroform	Chloroform	U		U		U	U
85535-85-9	Klorparaffiner C14-C17	Chloroparaffins C14-C17	U	S	S		U	
7790-94-5	Klorsulfonsyra 5%	Chlorosulphonic acid 5%				U		
7790-94-5	Klorsulfonsyra konc.	Chlorosulphonic acid conc.	U		U		U	
/	Kokosoljaalkoholist	Coconut oil alcoholic			S			
124-38-9	Koldioxid	Carbon dioxide	S		S	S	S	S
75-15-0	Koldisulfid	Carbon disulphide		O	S			
630-08-0	Kolmonoxid	Carbon monoxide			S			S
497-19-8	Kolsyra 5%	Carbonic acid 5%	S		S	S	S	S
497-19-8	Kolsyra konc.	Carbonic acid conc.	S		S		S	S
56-23-5	Koltetraklorid	Carbon tetrachloride		U	U			U
/	Konc. Detergenter	Conc. Detergents use	S	S		S	S	
/	Koncentrerade extrakt av cola	Concentrated extracts of cola			S			

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
544-92-3	Kopparcyanid	Copper cyanide sat. sol.			S			S
7789-19-7	Kopparfluorid	Copper fluoride			S			S
1344-67-8	Kopparklorid	Copper chloride sat. sol.			S			S
3251-23-8	Kopparnitrat	Copper nitrate			S			S
3251-23-8	Kopparnitrat mättad lösn.	Copper nitrate sat. sol.			S			
7758-98-7	Kopparsulfat mättad lösn.	Copper sulphate sat.sol.			S	S		S
/	Kresol	Cresol	U			U	U	U
7738-94-5	Kromsyra 5%	Chromic acid 5%	S		O	S	S	O
7738-94-5	Kromsyra 10%	Chromic acid 10%	O		O		O	O
7738-94-5	Kromsyra 50%	Chromic acid 50%			O			O
/	Kungsvatten	Water ragia			U			U
7727-37-9	Kväve	Nitrogen	S	S	S	S	S	
13257-51-7	Kvicksilver	Mercury			S			S
/	Lacker och lack lösningsmedel	Lacquers and lacquer solvents				S		
8006-54-0	Lanolin	Lanolin	S				S	
/	Lösningar för bly plätering	Solutions for lead plating			S			
/	Lösningar för förnickling	Solutions for nickel plating			S			
/	Lösningar för förtening	Solutions for tin plating			S			
/	Lösningar för förzinkning	Solutions for zinc plating			S			
/	Lösningar för guldplätering	Solutions for gold plating			S			
/	Lösningar för kadmium-beläggning	Solutions for cadmium plating			S			
/	Lösningar för kopparplätering	Solutions for copper plating			S			
/	Lösningar för mässing plätering	Solutions for brass plating			S			
/	Lösningar för silverplätering	Solutions for silver plating			S			
/	Luft	Air	S	S	S	S	S	
/	Lye	Lye			S			

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
/	Lye, alkaliska lösn.	Lye, alkaline soln.				S		
108-39-4	m-Kresol	m-Cresol		S				
13717-00-5	Magnesiumkarbonat	Magnesium carbonate			S			S
7487-88-9	Magnesiumsulfat	Magnesium sulphate			S			S
/	Majsolja	Corn oil			S			
74-82-8	Metan	Methane				S		
67-56-1	Methylic alkohol 5%	Methylic alcohol 5%	S	S	S		S	S
67-56-1	Methylic alkohol 6%	Methylic alcohol 6%		S	S	U		S
67-56-1	Methylic alkohol 50%	Methylic alcohol 50%		S	S			S
67-56-1	Methylic alkohol max. konc.	Methylic alcohol max conc.		S	S			S
79-20-9	Metylacetat	Methyl acetate			S			U
96-33-3	Metylakrylat	Methyl acrylate			S			
75-09-2	Metylenklorid	Methylene chloride		U		U		
78-93-3	Metyletylketon	Methylethylketone		O	U	S		U
74-88-4	Metyljodid	Methyl iodide		O				
74-87-3	Metylklorid	Methyl chloride				U		
80-62-6	Metylmetakrylat	Methyl methacrylate		S				
/	Mineral alkoholer	Mineral alcohols		U				
/	Mineralolja	Mineral oil		O	S		S	O
/	Mjölk	Milk			S			S
50-21-5	Mjölksyra vattenlös. 3%	Lactic acid aq. sol. 3%	S		S		S	S
50-21-5	Mjölksyra vattenlös. 10%	Lactic acid aq. sol. 10%	S		S	poliether S poliester O	S	S
64-18-6	Myrsyra 10%	Formic acid 10%	O	S	S	U	O	S
64-18-6	Myrsyra 20%	Formic acid 20%	O	S	S	U	O	
64-18-6	Myrsyra 25%	Formic acid 25%	U	S	S	U	U	
64-18-6	Myrsyra 85%	Formic acid 85%	U	S	S	U	U	U

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
64-18-6	Myrsyra konc.	Formic acid conc.	U	S	S	U	U	U
71-41-0	n-Amylalkohol	n-Amyl alcohol		S				
71-36-3	n-Butanol	n-Butanol		S	S			
124-18-5	n-Dekan	n-Decane		U				
142-82-5	n-Heptan	n-Heptane			U			
110-54-3	n-Hexan	n-Hexane		U				
111-65-9	n-Oktan	n-Octane		U				
617-84-5	N, N'-dietylformamid	N,NÖ-diethylformamide		S				
/	Nafta	Naphtha			O	O		O
91-20-3	Naftalen	Naphthalene		U				
14217-21-1	Natrium-ferricyanid	Sodium ferricyanide			S			S
1313-82-2	Natrium-sulfid	Sodium sulphide			S			S
127-09-3	Natriumacetat	Sodium acetate	S		S		S	S
532-32-1	Natriumbensoat	Sodium benzoate			S			S
144-55-8	Natriumbikarbonat	Sodium bicarbonate			S			S
7789-12-0	Natriumbikromat	Sodium bichromate			S			
7681-38-1	Natriumbisulfat	Sodium bisulphate			S			S
7631-90-5	Natriumbisulfit	Sodium bisulphite			S			S
1303-96-4	Natriumborat	Sodium borate			S			
7647-15-6	Natriumbromid	Sodium bromide			S			S
143-33-9	Natriumcyanid	Sodium cyanide			S			
7681-49-4	Natriumfluorid	Sodium fluoride			S			
1310-73-2	Natriumhydroxid 5%	Sodium hydroxide 5%	S	S	S	S	S	S
1310-73-2	Natriumhydroxid 10%	Sodium hydroxide 10%	S	S	S	O	S	S
1310-73-2	Natriumhydroxid 20%	Sodium hydroxide 20%	S	S	S	U	S	S
1310-73-2	Natriumhydroxid 50%	Sodium hydroxide 50%			S	U		S

	S: Resistent Ö: Begränsad resistent U: Inte resistent	S Resistant Ö Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
1310-73-2	Natriumhydroxid konc.	Sodium hydroxide conc.			S	U		
7681-52-9	Natriumhypoklorit 14% cl2	Sodium hypochlorite 14% cl2	S	S	S	U	S	S
7681-52-9	Natriumhypoklorit 15% cl2	Sodium hypochlorite 15% cl2	S		S	U	S	S
497-19-8	Natriumkarbonat	Sodium carbonate	S		S		S	S
7775-09-9	Natriumklorat	Sodium chlorate			S			
7647-14-5	Natriumklorid 20%	Sodium chloride 20%	S	S	S		S	
7647-14-5	Natriumklorid 25%	Sodium chloride 25%	S		S	Ö	S	
7647-14-5	Natriumklorid konc.	Sodium chloride conc.	S		S		S	
7631-99-4	Natriumnitrat	Sodium nitrate			S	S		S
15124-09-1	Natriumsulfat	Sodium sulphate			S			S
7772-98-7	Natriumtiosulfat	Sodium thiosulphate				S		
/	Naturgas	Natural gas				Ö		
13138-45-9	Nickel-nitrat	Nickel nitrate			S			S
7718-54-9	Nickelklorid	Nickel chloride			S			S
15244-37-8	Nickelsulfat	Nickel sulphate			S			S
22083-74-5	Nikotin	Nicotine			S			S
98-95-3	Nitro-etan	Nitrobenzene			U			
79-24-3	Nitrobensen	Nitro-ethane		Ö				
/	öl	Beer			S			S
8014-95-7	Oleum	Oleum				U		U
/	Olivolja	Olive oil		U	Ö			
/	Olje bränsle	Oil fuel				S	S	
112-80-1	Oljesyra	Oleic acid				S		U
/	Organiska acetater	Organic acetates				S		
144-62-7	Oxalsyra	Oxalic acid			S			S
10028-15-6	Ozon	Ozone			Ö	S		U

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
57-10-3	Palmitinsyra	Palmitic acid				O		O
109-66-0	Pentan	Pentane				U		
79-21-0	Perättiksyra	Peracetic acid	U	U	O	U	U	
127-18-4	Perkloretylen	Perchloroethylene		U	U	U		
7601-90-3	Perklorosyra	Perchloric acid			S	S		S
/	Petroleum	Petroleum				O		
88-89-1	Pikrinsyra(acq.)	Picric Acid (acq.)			S			S
/	Propan	n-Propanol			S			S
40811-14-1	Propan	Propane				S		O / U
471-25-0	Propargylic syra	Propargylic acid			S			S
79-09-4	Propionsyra	Propionic acid		S				
107-12-0	Propionitrile	Propionitrile		U	U			
78-87-5	Propylendiklorid (100 %)	Propylene dichloride (100%)			U			
57-55-6	Propylenglykol	Propylene glycol			S			
75-56-9	Propylenoxid	Propylene oxide		O				
79-09-4	Propylic syra	Propylic acid			S			
110-86-1	Pyridin	Pyridine		S	U			
/	Rengöringsmedel, syntetiska	Detergents, synthetic			S			
108-46-3	Resorcinol	Resorcinol			S			
8001-79-4	Ricinolja	Castor oil			S			O
69-72-7	Salicylsyra	Salicylic acid			S			S
7697-37-2	Salpetersyra 5%	Nitric acid 5%	S	S	S	O	S	S
7697-37-2	Salpetersyra 10%	Nitric acid 10%	S	S	S	U	O	S
7697-37-2	Salpetersyra 20%	Nitric acid 20%	S	S	S	U	U	S
7697-37-2	Salpetersyra 30%	Nitric acid 30%	S	O	O	U	U	O
7697-37-2	Salpetersyra 50%	Nitric acid 50%	S	O	O	U	U	O

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
7697-37-2	Salpetersyra 70%	Nitric acid 70%	U	U	U	U	U	O
7697-37-2	Salpetersyra 95%	Nitric acid 95%	U	U	U	U	U	U
7647-01-0	Saltsyra 5%	Hydrochloric acid 5%	S	S	S	S	S	S
7647-01-0	Saltsyra (torr gas)	Hydrochloric acid (dry gas)			S			
7647-01-0	Saltsyra 20%	Hydrochloric acid 20%	S	S	S	U	S	S
7647-01-0	Saltsyra 22%	Hydrochloric acid 22%	S		S	U	S	S
7647-01-0	Saltsyra konc.	Hydrochloric acid conc.	S	S	S	U	S	S
7783-08-6	Selensyra	Selenic acid			S			
/	Silikon fetter	Silicone fats				S		
/	Silikonolja	Silicone oil		U	S	S		S
7761-88-8	Silverniträt	Silver nitrate			S			S
/	Smörjolja (petroleum)	Lubricant oils (petroleum)				O		
107-92-6	Smörsyra 20%	Butyric acid 20%	S	S	S		S	
107-92-6	Smörsyra konc.	Butyric acid conc.		S	S			
/	Stärkelse (mättad lösn.)	Starch (sat.sol.)			S			
57-11-4	Stearinsyra	Stearic acid	S		S		S	
7446-09-5	Svaveldioxid (akv.)	Sulphur dioxide (acq.)			S			S
8014-95-7	Svavelsyra 5%	Sulphuric acid 5%	S	S	S	S	S	S
8014-95-7	Svavelsyra 20%	Sulphuric acid 20%	S	S	S	U	S	S
8014-95-7	Svavelsyra 25%	Sulphuric acid 25%	S	S	S	U	S	S
8014-95-7	Svavelsyra 50%	Sulphuric acid 50%	O	S	S	U	O	S
8014-95-7	Svavelsyra 70%	Sulphuric acid 70%	U	S	S	U	U	O
8014-95-7	Svavelsyra 80%	Sulphuric acid 80%	U	S	S	U	U	O / U
8014-95-7	Svavelsyra 96%	Sulphuric acid 96%	U	S	O	U	U	O / U
8014-95-7	Svavelsyra 98%	Sulphuric acid 98%	U	S	O	U	U	O / U
8014-95-7	Svavelsyra konc. gasform	Sulphuric acid conc. fuming	U		U	U	U	U

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
7782-99-2	Svavelsyrlighet	Sulphurous acid			S			O
7782-44-7	Syre	Oxygen	S	S	S	S	S	S
7772-99-8	Tennklorid (II)	Tin chloride (II)			S			
7646-78-8	Tennklorid (IV)	Tin chloride (IV)			S			
8006-64-2	Terpentin	Turpentine		U	U	S		U
109-99-9	Tetrahydrofuran	Tetrahydrofuran		O	U	U		O / U
7550-45-0	Titantetraklorid	Titanium tetrachloride			U			
108-88-3	Toluen	Toluene			U	U		U
/	Transformatorolja	Transformer oil		U	S			O / U
102-71-6	Trietanolamin	Triethanolamine			S	U		O
112-27-6	Trietylenglykol	Triethylene Glycol			S			
79-01-6	Trikloretylen	Trichloroethylene		U	U			U
67-66-3	Triklormetan	Trichloromethane		U				
7601-54-9	Trinatriumfosfat	Trisodium phosphate			S			S
3319-31-1	Trioctyl Trimellitate (TOTM)	Trioctyl Trimellitate (TOTM)	U	S	S		U	
/	Tvållösning (samtl. konc.)	Soap solution (all conc.)			S	S		S
57-13-6	Urea (AD BLÅ) *	Urea (AD BLUE) *	S		S	S	S	S
/	Urin	Urine			S			
69-93-2	Urinsyra	Uric Acid			S			S
/	Utvecklare (fotografisk)	Developers (photographic)			S			
/	Vanilj	Vanilla			S			
/	Vassle	Whey			S			S
1333-74-0	Väte	Hydrogen			S	S		
7722-84-1	Väteperoxid 30 vol.	Hydrogen peroxide 30 vol.	S				S	S
7783-06-4	Vätesulfidgas	Hydrogen sulphide gas	S				S	S
109-86-4	Vatten	Water	S	S	S	S	S	S

	S: Resistent O: Begränsad resistent U: Inte resistent	S Resistant O Restricted Resistant U Not resistant	ANVÄNDNING					
CAS. N.	KEMIKALIER	CHEMICALS	PVC	TPV	LLDPE	PU	PVC OIL	EVA
/	Vegetabiliska oljor	Vegetable oils				S		
/	Vin	Wines			S			
/	Vinäger	Vinegar			S			
108-05-4	Vinylacetat	Vinyl acetate			S			U
5892-10-4	Vismut -karbonat	Bismuth carbonate sat. sol.			S			S
/	Wiskey	Wiskey			S			
1330-20-7	Xylen	Xylene		U	U	U		U
7699-45-8	Zinkbromid	Zinc bromide			S			
3486-35-9	Zinkkarbonat	Zinc carbonate			S			
1314-13-2	Zinkklorid	Zinc oxide			S			
7646-85-7	Zinkklorid 20%	Zinc chloride 20%	S	S	S		S	S
7646-85-7	Zinkklorid konc.	Zinc chloride conc.	S		S		S	S
557-05-1	Zinkoxid	Zinc stearate			S			
7733-02-0	Zinkstearat	Zinc sulphate		U	S	U		S

ALL TEKNISK DATA GÄLLER VID EN TEMPERATUR PÅ 23°. TOLERANS PÅ ALLA VÄRDEN ±5%.
Den här tabellen är bara för kemisk resistens, inte för kontakt med livsmedel. (Ed.1 22/09/2010)

Konc.: Koncentrerad.
Samtl. konc.: Samtliga koncentrationer.
Max. konc.: Maximal koncentration.
Mättad lösn.: Mättad lösning.
Vatten lösn.: Vattenhaltig lösning
Be: Baumé.

För gaserna, endast den kemisk resistensen anges: uppgifter som inte avses permabilitet.

* AD BLUE är ett handelsnamn för hög renhet urea, 32,5% i vatten.

LÄMPLIGHETEN AVSER INNERTUBEN PÅ SLANGEN

TOTAL TECHNICAL APPLICATIONS APPLY TO A TEMPERATURE OF 23°. TOLERANCE ON ALL SPECIFICATIONS ±5%.
This Table is only for chemical resistance, not for food contact. (Ed.1 22/09/2010)

Conc.: Concentrated.
All conc.: All the concentrations,
Max conc.: Maximun concentration,
Sat. Sol.: Saturated Solution,
Aq. sol.: Aqueous solution,
Bé: Baumé.

For the gases, only the chemical resistance is indicated: data not referred to permeability.

* AD BLUE is a commercial name for high purity UREA, 32,5 % in water.

THE SUITABILITY REFERS TO THE LINING OF THE HOSE.