

Ø nominal mm	Ø nominal inch	Ø i.d. mm	Ø o.d. mm	vacuum 23 °C m/H <sub>2</sub> O	working press. at 23 °C r.1:3 bar	working press. at 23 °C r.1:4 bar	working press. at 60 °C bar	bursting press. at 23 °C bar	bending radius mm	total thickness mm	Ø steel wire mm	spiral pitch mm	spiral direction	weight meter g/m	coil length m	Availability
19	3/4	19	27.5	9	25	15	14	80	100	4.5	0.8	5.5	right	340	60	In stock
25	1	25	33.5	9	25	15	14	77	120	4.3	1	7.5	right	430	60	In stock
28.5		28.5	37.5	9	20	15	14	65	130	4.5	1.2	8.5	right	550	60	On demand
32	1 1/4	32	41	9	18	14	14	56	150	4.5	1.2	9.5	right	590	60	In stock
38	1 1/2	38	48.5	9	17	13	13	53	200	5.3	1.4	10	right	800	30	In stock
51	2	51	62.5	9	14	10	13	42	250	5.8	1.6	11.5	right	1150	30	In stock
63	2 1/2	63	74.5	9	12	10	11	40	300	5.8	1.6	12	right	1450	30	In stock

All technical specifications apply to a temperature of 23° C ± 2° C (ISO 291)

All technical specifications contained herein are provided for reference purposes only.

For further details regarding our products' specifications, please refer to the relevant products' data sheets or contact your sales representative.