

Ø nominal mm	Ø nominal inch	Ø i.d. mm	Ø o.d. mm	vacuum 23 °C m/H ₂ O	working press. at 23 °C r.1:3 bar	working press. at 23 °C r.1:4 bar	bursting press. at 23 °C bar	bending radius mm	total thickness mm	Ø steel wire mm	spiral pitch mm	spiral direction	weight meter g/m	coil length m	Availability
19	3/4	19	28	9	16	12	48	70	4.5	1	8.5	right	450	60	In stock
25	1	25	35.5	9	16	12	48	80	5.3	1.2	9	right	670	60	In stock
30		30	40.5	9	16	12	48	90	5.3	1.2	9	right	770	60	On demand
32	1 1/4	32	42.5	9	16	12	48	100	5.3	1.2	9	right	800	60	In stock
35		35	47	9	14	10	42	120	6	1.4	9	right	1050	60	On demand
38	1 1/2	38	51	9	14	10	42	125	6.5	1.4	9	right	1200	40	In stock
40		40	53.5	9	14	10	42	130	6.8	1.4	9	right	1200	40	On demand
45	1 3/4	45	58	9	12	10	36	140	6.5	1.4	9	right	1340	40	On demand
50	2	50	64	9	12	10	36	150	7	1.6	9	right	1730	40	In stock
60		60	74	9	12	10	36	180	7	1.6	9	right	1950	40	In stock
63	2 1/2	63	77	9	12	10	36	190	7	1.6	9	right	2030	40	In stock

All technical specifications apply to a temperature of 23° C ± 2° C (ISO 291)

All technical specifications contained herein are provided for reference purposes only.

For further details regarding our products' specifications, please refer to the relevant products' data sheets or contact your sales representative.