

Nenn-Ø mm	Innen-Ø mm	Aussen-Ø mm	Betriebsdruck bei 23 °C bar	Platzdruck bei 23 °C bar	Gesamtstärke mm	Gewicht je Meter g/m	Bruchlast bei Zugbeanspruchung kg	Beschaffbarkeit
20	20		30	90	min. 2.1	230	1200	Ab lager
25	25		30	90	min. 2.0	260	1350	Ab lager
38	38		20	62	min. 2.0	345	2200	Ab lager
45	45		20	62	min. 2.0	380	3300	Ab lager
52	52		20	60	min. 2.0	470	4300	Ab lager
70	70		17	50	min. 2.3	680	6500	Ab lager
75	75		17	50	min. 2.3	790	7200	Auf anfrage
102	102		17	50	min. 2.5	1080	10500	Auf anfrage
110	110		15	45	min. 2.5	1160	11000	Auf anfrage
150	150		13	35	min. 2.6	1650	16500	Auf anfrage

All technical specifications apply to a temperature of 23° C ± 2° C (ISO 291)

All technical specifications contained herein are provided for reference purposes only.

For further details regarding our products' specifications, please refer to the relevant products' data sheets or contact your sales representative.