

Ø nominal mm	Ø nominal inch	Ø i.d. mm	Ø o.d. mm	working pressure at 23 °C bar	vacuum 23 °C m/H <sub>2</sub> O	bursting press. at 23 °C bar	bending radius mm	total thickness mm	Ø rigid spiral (AxB if oval) mm	spiral pitch mm	spiral direction	weight meter g/m	coil length m	Availability
19		19	24.6	6.5	7	19.5	60	2.8	2.3x3.5	7	right	250	50	On demand
20		20	26.2	6.5	7	19.5	65	3.1	2.5x4	7	right	275	50	In stock
25	1	25	31.6	6.5	7	19.5	100	3.3	3.2	7.4	right	330	50	In stock
30		30	37	5.5	7	16.5	125	3.5	3.4	7.5	right	420	50	In stock
32	1 1/4	32	39.2	5.5	7	16.5	135	3.6	3.6x3.4	7.7	right	460	50	In stock
35		35	41.8	5	7	15	145	3.4	3.3	7.7	right	500	50	In stock
38	1 1/2	38	45.4	4.5	7	13.5	155	3.7	3.6	7.6	right	550	50	In stock
40		40	47.8	4.5	7	13.5	160	3.9	3.6	7.8	right	610	50	In stock
45	1 3/4	45	52.8	4	7	12	180	3.9	3.6	8	right	670	50	In stock
50	2	50	58.2	3.5	7	10.5	200	4.1	4	8.3	right	810	50	In stock
51	2	51.3	59.5	3.5	7	10.5	225	4.1	3.9	8.5	right	810	50	On demand
55		55	63.6	3.5	7	10.5	225	4.3		9.8	right	860	50	On demand
60		60	69	3.5	7	10.5	245	4.5	4.4	8.3	right	970	50	In stock
63	2 1/2	63	71.2	3.5	7	10.5	260	4.1	3.9	8.5	right	1040	50	In stock
70		70	79	3.5	7	10.5	290	4.5	4.1	9	right	1200	50	On demand
75		75	85.4	2.5	7	7.5	315	5.2	4.9	9.1	right	1380	50	In stock
76	3	76	86	2.5	7	7.5	320	5		12	right	1380	50	In stock
80		80.2	90.8	2.5	7	7.5	325	5.3	5	10.5	right	1560	25	In stock
90	3 1/2	90	100.4	2.5	7	7.5	390	5.2	5	10.9	right	1800	25	On demand
100		100	112	2.5	7	7.5	430	6		11.3	right	2160	25	On demand
102	4	102.3	113.9	2.5	7	7.5	430	5.8	5.6	11.5	right	2200	25	In stock
110		110	122	2.5	5	7.5	480	6	5.6	11.5	right	2400	25	On demand
120		120	132.4	2.5	5	7.5	610	6.2		11.5	right	2850	25	On demand
125		125	137.6	2	5	6	660	6.3		11.6	right	3130	25	On demand
127	5	127	140.6	2	5	6	670	6.8		12.3	right	3130	25	In stock
150		150	164.4	2	5	6	730	7.2		14	right	4250	25	On demand
152	6	152.4	167.2	2	5	6	750	7.4		14.5	right	4250	25	In stock
200		200	218.2	1	5	3	810	9.1		21.5	right	6400	20	On demand
204	8	203.2	221.2	1	5	3	810	9	8.4	22	right	6400	20	On demand

All technical specifications apply to a temperature of 23° C ± 2° C (ISO 291)

All technical specifications contained herein are provided for reference purposes only.

For further details regarding our products' specifications, please refer to the relevant products' data sheets or contact your sales representative.