

Ø nominal mm	Ø i.d. mm	Ø o.d. mm	working pressure at 23 °C bar	vacuum 23 °C m/H ₂ O	bursting press. at 23 °C bar	bending radius mm	total thickness mm	Ø rigid spiral (AxB if oval) mm	spiral pitch mm	spiral direction	weight meter g/m	Segment Length m	coil length m	Availability
50	50	60.6	4.5 (*)	9	13.5 (*)	350	5.3	5	10.5	right	1050		50	On demand
60	60	70.8	4	9	12	420	5.4	5x5.6	11	right	1250		50	On demand
70	70	82	3.5	9	10.5	490	6	5.6	12.3	right	1600		50	On demand
75	75	88	3.5	9	10.5	525	6.5	6	13	right	1650		50	On demand
80	80	93	3.5	9	10.5	560	6.5	6	14	right	1750		50	On demand
90	90	103.4	3	9	9	630	6.7	6.2	14	right	2150		30	On demand
100	100	113.6	3	9	9	700	6.8	6.5	14.5	right	2650		30	On demand
110	110	124.4	3	9	9	800	7.2	6.8	15.5	right	2950		30	On demand
125	125	141.6	2.5	9	7.5	875	8.3	7.8	17.5	right	3600		30	On demand
150	150	168	2 (*)	9 (*)	6 (*)	1050	9	8.6	20	right	4900		30	On demand
200	200	226	1.5 (*)	9 (*)	4.5 (*)	1400	13	12	22.5	right	9500	10		On demand

All technical specifications apply to a temperature of 23° C ± 2° C (ISO 291)

All technical specifications contained herein are provided for reference purposes only.

For further details regarding our products' specifications, please refer to the relevant products' data sheets or contact your sales representative.